



Pontoon LINK

Pontoon LINK is for making inflatable dinghies with flat or domed pontoon ends compatible with Dinghy Rings.

Included: Two Pontoon LINKs

Materials and tools needed:

Acetone or PVC Primer (e.g. Polymarine 2903)
PVC 2-component adhesive (e.g. Polymarine 3026)
Hypalon 2-component adhesive (only if the boat is made of Hypalon)
Brush, Pen, Cloth, Soft edge scraper

Important:

Find out if your dinghie is made of PVC or Hypalon.

Before starting to glue, note that your workplace must be well ventilated, hot and dry, 18-25 degrees C. If the air is damp, the glue can not be used.

Do not use any open flame, as solvents are highly flammable.

Do not use any adhesive that has been mixed for more than 4 hours.

Do not use sandpaper on PVC fabrics.

If you have a Hypalon boat, the contact surfaces of the pontons shall be easily sanded with sandpaper and primed with 2-component Hypalon adhesive before step 9. You will then apply a thin layer of Hypalon adhesive as a primer and allow it to dry. Then you apply PVC glue on top of that.

Don't touch cleaned surfaces with your hands! Grease will weaken the bonding.



1. Make sure your inflatable has a proper pressure in all air chambers.



4. A lip up to 3 mm is ok. If the lip stand out more, material must be cut out of LINK



2. Clean the surface where LINK is to be mounted. Make sure the surface is completely dry.



5. Wipe the edge that will attach to the pontoon with acetone. Wipe twice until the surface is sticky.



3. Align LINK so that it is centered on the pontoon. Mark with a pen.



6. Wipe with acetone the area where LINK will be attached to the pontoon.



7. Mix the 2-component adhesive according to the instructions.



8. Apply a first thin layer of glue to the edge of the LINK.



Apply a first thin layer of glue to the pontoon, where LINK should be installed.



10. Wait 30 minutes until the glue has dried.



11. Apply a second thin layer of glue to the LINK.



12. Apply a second thin layer of glue to the pontoon, where LINK should be installed.



13. Wait five minutes, put together the pieces when the glue is sticky. It bonds directly.



14. Press firmly for a few minutes.



15. Use a scraper to press the edges. Work from the middle and out to remove air bubbles.



16. If the glue does not stick well, heat with a hot air gun and press together again.



17. Wipe off marks and excess glue with acetone as soon as possible.



18. Wait at least 6 hours before touching LINK. The adhesive has hardened after 48 hours.



19. If there is a gap or leap near the lip, drill a 5 mm hole in the bottom of the LINK.



20. The hole allows water to drain out.



21. LINK should now fit into Dinghy Rings with a 5 mm gap.

Pontoon LINK Made in Ukraine

Material: PVC, shall be recycled as plastic

Contact: Dinghy Rings Sweden AB, info@dinghyrings.se, +46 10-164 04 00, www.dinghyrings.com